

### Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in this application:

#### Listing of Claims:

Claim 1 (Cancelled).

Claim 2 (Previously presented): The thermoplastic molding composition according to Claim 5, wherein the average particle diameter of the compound is 1 nm - 10  $\mu$ m.

Claim 3 (Previously presented): The thermoplastic molding composition according to Claim 5, wherein the average particle diameter of the compound is 5-500 nm.

Claim 4 (Cancelled).

Claim 5 (Currently amended): A thermoplastic molding composition comprising:  
40 to 99 parts by wt. aromatic polycarbonate;  
~~0-1~~ to ~~50-30~~ parts by wt. vinyl copolymer;  
0.5 to 60 parts by wt. graft polymer; and  
0.1 to 30 parts by wt. aluminum compound selected from the group consisting of water-containing oxides, phosphates, sulfates, sulfides, hydroxides, borates and borophosphates of aluminium and having an average particle diameter of 1 nm - 20  $\mu$ m.

Claim 6 (Cancelled).

Claim 7 (Currently amended): A thermoplastic molding composition comprising:  
40 to 99 parts by wt. aromatic polycarbonate;  
~~0-1~~ to ~~50-30~~ parts by wt. vinyl copolymer;  
0.5 to 60 parts by wt. graft polymer which is a product of copolymerization of 5 to 95 parts by wt. of a mixture of

50 to 95 parts by wt. styrene,  $\alpha$ -methylstyrene, styrene substituted on the nucleus by halogen or alkyl, C<sub>1</sub>-C<sub>8</sub>-alkyl methacrylate, C<sub>1</sub>-C<sub>8</sub>-alkyl acrylate or mixtures thereof, and

5 to 50 parts by wt. acrylonitrile, methacrylonitrile, C<sub>1</sub>-C<sub>8</sub>-alkyl methacrylate, C<sub>1</sub>-C<sub>8</sub>-alkyl acrylate, maleic anhydride, C<sub>1</sub>-C<sub>4</sub>-alkyl or phenyl-N-substituted maleimide or mixtures thereof or 5 to 95 parts by weight of a polymer having a glass transition temperature below -10°C; and

0.1 to 30 parts by wt. aluminum compound selected from the group consisting of water-containing oxides, phosphates, sulfates, sulfides, hydroxides, borates and borophosphates of aluminium and having an average particle diameter of 1 nm - 20  $\mu$ m.

**Claim 8 (Previously presented):** The thermoplastic molding composition of Claim 5 further including at least one additive selected from the group consisting of stabilizers, pigments, mold release agents, flow auxiliaries and antistatics.

**Claim 9 (Previously presented):** The thermoplastic molding composition of Claim 5 further including at least one additive selected from the group consisting of fillers, reinforcing materials and inorganic compounds.

**Claims 10 and 11 (Cancelled).**

**Claim 12 (Previously presented):** In a method of producing a molded article, the improvement comprising including the thermoplastic molding composition of Claim 5.

**Claim 13 (Previously presented):** The molded article prepared by the method of Claim 12.